



## Swift®tak 5701

**Тип клея**

Клей на водной основе

**Преимущества продукта**

- хорошая схватываемость влажного клея
- среднее открытое время
- очень хорошая перерабатываемость
- хорошая влагостойкость

**Типичные области применения**

Разработан для применений, где необходима хорошая влагостойкость финальной склейки. Типичные применения включают боковой шов картонных коробок, бумажные трубочки, навивные втулки и т.д.

**Применимые основы**

Гофрокартон с крафтлайнером, тестлайнером или картоном. Бумага 100-120г/м<sup>2</sup> – 60г/м<sup>2</sup> с или без влагопрочной обработки (бумажные трубочки).

Перед применением необходимо проведение соответствующего тестирования.

**Типичные свойства**

Свойство	Значение
Цвет	белый
Плёнка	эластичная
pH	прибл.4.5
Содержание твёрдых частиц	прибл. 46%
Вязкость (Brookfield RVT-Туре: Sp3, при 20°C)	прибл. 3650 mPa.s
Срок хранения	6 месяцев



# H.B. Fuller



## TECHNICAL DATA SHEET

### Инструкции по применению

Применим для всех стандартных систем нанесения: форсунки, щелевые, колёса и диски.

При производстве трубочек – открытая ванна с валом и скребком.

### Инструкции по очистке

По возможности остатки клея должны быть смыты холодной водой до высыхания. Удаление остатков засохшего клея может быть затруднительно и потребовать использования тёплой мыльной воды и механического соскребания.

### Стандартная упаковка

Пожалуйста, обратитесь в Ваш местный офис продаж для получения информации о доступных решениях по очистке.

### Условия хранения

Чистые и сухие условия, при температуре выше +5°C и ниже +35°C. Ёмкость с клеем должна быть герметично закрыта для предотвращения высыхания при хранении. После открытия упаковки убедитесь, что крышка заменена, и ёмкость закрыта в ходе работы.

### Рекомендации по утилизации

См. сертификат безопасности материала для получения инструкций по утилизации.

### Рекомендации по безопасности

См. сертификат безопасности материала для получения инструкций по безопасности..

## Our Focus is Clear. Perfecting Adhesives.

**IMPORTANT:** The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.



## H.B. Fuller

**H.B. Fuller Company**

info-europe@hbfuller.com  
www.hbfuller.com/  
eimea/contact-us